

Product Specification*Product: ONGRODUR I normal impact resistant, industrial, rigid, Ca-Zn stabilized sheet***Quality Requirements**

№	Analysed Parameters	Unit	Requirements of Approval	Standards
1.	Appearance	-	<p>The surface is homogeneous, consistently coloured.</p> <p>The colour matches with the etalon.</p> <p>The cutting surfaces are without/free from chips, splits and sawdust.</p> <p>Checking of the surface quality should be carried out by scrutiny from the distance of 1 m at right angles to surface in natural adequate light. With this scrutiny the surface is free from optical defects, streaks of light. The sheet is perfect flat</p> <p>The quality of the top and back side of the sheets might be different due to the technology.</p> <p>In order to protect the surface quality we use protective film.</p>	OPV-009
2.	Dimensions			OPV-010
2.1.	Length	mm	1000 – 3050 + 5,0 - 1,0	
2.2.	Width	mm	1000 - 1200 + 2,0 - 1,0 1201 - 1500 + 2,5 - 1,0 1501 – 2050 + 3,0 – 1,0	
2.3.	Thickness (S)	mm	1,0 - 20;	
2.4	Thickness tolerance ≤ 4 Thickness tolerance > 4	mm mm	$S \pm (0,1 + 0,05 S)$ $S \pm (0,08 + 0,03 S)$	

Product Specification*Products: ONGRODUR I normal impact resistant, industrial, rigid, Ca-Zn stabilized sheet***Quality Requirements**

№	Analysed Parameters	Unit	Requirements of Approval	Standards
3.	Deviation from the right angle	mm	Max. 3 mm/1000 mm	OPV-012
4.	Tensile Strength	MPa	min. 45	MSZ EN ISO 527-1
5.	Elongation at Break	%	Informative Data	MSZ EN ISO 527-2 MSz EN ISO 527-3
6.	Colour deviation		$\Delta E \leq 1,5$	DIN 6174
7.	Storing		Sheets have to be stored in dry place with good airing. The product has to be protected against exposure like sunshine and damp. Due to exaggerated temperature the sheets might deform. This fact has to be taken into consideration during the logistics processes. There can be max. 6 pallets taken on the top of each other.	

Date: 02-08-2018

Issue: 8.

Amendments: points 2.1 and 2.2

Validation:

Issued by:: Motkóné Lauer Katalin Head of QA

Countersigned : Szabó Gyula managing director