

TEC LUX 202 Matt

Product Information

Polimeric PVC (transparent gloss, $80~\mu$) with an ultra clear acrylic dispersion adhesive (permanent), laminated on a two-sided clay-coated and double-sided siliconized paper liner (120 g/m²).

Tec Lux 202 Matt offers an excellent dimensional stability and increases image brightness.

Laminating film, suitable for protection of digital prints and images to avoid infuence of UV, dirt and humidity.

Tec Lux 202 Matt improves outdoor print duration and reduces fading and damage of the prints due to weather conditions.

Particularly suitable for application on flat, curved and slightly curved surfaces.

Shelf Life

2 years when stored in the original packaging between 20°C and 25°C at 50% relative humidity.

Recommendations for laminating

Please make sure that the print is perfectly dry before laminating.

We suggest to let the material dry for at least 48 hours after printing.

Technical Data

Carrier: Monomeric PVC, highly stabilized,

calendered

Thickness: 80 μ +/- 5 %

Adhesive: ultra clear acrylic

dispersion, permanent

Adhesión [N/cm]: 4,3 +/- 5 %

Liner: two-sided clay-coated

double-sided siliconized

paper (120 g/m²)

Application temperature: +10 - +40 °C

Service temperature: - 20 - +50 °C

Outdoor durability: 1 year

Standard Dimensions

1050 mm x 50 m 1370 mm x 50 m

1550 mm x 50 m

Safety Data Sheet

When used under normal conditions, this product does not generate or release any dangerous substances or hazardous chemicals. This is a non-hazardous product in accordance with the current GefStoffV and EU criteria. Therefore it is not necessary to prepare a Material Safety Data Sheet for this product. The Safety Data Sheet serves only to comply with the regulation to supply information in accordance with REACH Regulation (EC) No. 1907/2006 and is available on request.

This product is not a hazardous product with regards to transportation legislation; neither does it contain substances that are hazardous to water within the meaning of the federal water act. After use, dispose of the

KEMICA S.r.I.

Via F.Ili Rusjan, 76 - Frazione Rupa 34070 Savogna d'Isonzo (GO) - ITALIA

Phone: +39 0481 882 501 Fax: +39 0481 882 440

E-Mail: info@kemicasrl.it Internet: www.kemica.it

01/01/2016

The following technical details are issued to the best of our knowledge, however, without any responsibility for results due to several different kinds of material and application processes. Therefore, we highly recommend that before every usage a test should be conducted on the original material..